

AD-A152 989

ELECTROCHEMISTRY OF POLYMER FILMS NOT IMMERSSED IN  
SOLUTION ELECTRON TRANS..(U) NORTH CAROLINA UNIV AT  
CHAPEL HILL DEPT OF CHEMISTRY R W MURRAY ET AL.  
05 MAR 85 TR-13 N00014-82-K-0337


1/1

UNCLASSIFIED

F/G 7/4

NL

									END DATE INDEXED G O
--	--	--	--	--	--	--	--	--	-------------------------------



MICROCOPY RESOLUTION TEST CHART  
NATIONAL BUREAU OF STANDARDS-1963-A

2

OFFICE OF NAVAL RESEARCH  
Contract N00014-892-K-03337  
TECHNICAL REPORT # 13

Electrochemistry of Polymer Films not Immersed in Solution: Electron  
Transfer on an Ion Budget

by

Royce W. Murray, Principal Investigator

Prepared for Publication

in the

Journal of the American Chemical Society

University of North Carolina  
Department of Chemistry  
Chapel Hill, North Carolina 27514

March 5, 1985

DTIC  
ELECTE  
APR 25 1985  
S D E

Reproduction in whole or in part is permitted for  
any purpose of the United States Government

\*This document has been approved for public release  
and sale; its distribution is unlimited.

AD-A152 989

DTIC FILE COPY

85 04 01 130

1. REPORT NUMBER		2. SOVT ACCESSION NO.	3. RECIPIENT'S CATALOG NUMBER
Technical Report #13			
4. TITLE (and Subtitle)			5. TYPE OF REPORT & PERIOD COVERED
Electrochemistry of Polymer Films not Immersed in Solution: Electron Transfer on an Ion Budget			
7. AUTHOR(s)			6. PERFORMING ORG. REPORT NUMBER
J. C. Jernigan, C. E. D. Chidsey and R. W. Murray			
9. PERFORMING ORGANIZATION NAME AND ADDRESS			8. CONTRACT OR GRANT NUMBER(s)
Department of Chemistry University of North Carolina Chapel Hill, North Carolina 27514			N00014-892-K-03337
11. CONTROLLING OFFICE NAME AND ADDRESS			10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS
Office of Naval Research Department of the Navy Arlington, Virginia 22217			
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)			12. REPORT DATE
			13. NUMBER OF PAGES
			15. SECURITY CLASS. (of this report)
			Unclassified
			15a. DECLASSIFICATION/DOWNGRADING SCHEDULE
15. DISTRIBUTION STATEMENT (of this Report)			
Approved for Public Release, Distribution Unlimited			
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)			
18. SUPPLEMENTARY NOTES			
19. KEY WORDS (Continue on reverse side if necessary and identify by block number)			
electrochemistry, osmium, polymer film, ionic conductor			
20. ABSTRACT (Continue on reverse side if necessary and identify by block number)			
<p>Films of poly-[Os(bpy)<sub>2</sub>(vpy)<sub>2</sub>](ClO<sub>4</sub>)<sub>2</sub> sandwiched between two metallic electrodes can support electron hopping, concentration gradient-driven electron conduction in acetonitrile vapor and in dry N<sub>2</sub> gas, when the potential difference ΔE between the electrodes is made such as to generate a mixture of Os(III), Os(II), and Os(I) states. The latter requirement is dictated by the fixed pool (ion budget) of ClO<sub>4</sub><sup>-</sup> counterions in the film. It is significant that ClO<sub>4</sub><sup>-</sup> ions can move relatively freely in the dry film, that the apparent Os(III/II) and Os(II/I) formal potentials are different for the vapor and dry N<sub>2</sub> environments, and that currents through dry polymer films are larger than in vapor-exposed films.</p>			

ELECTROCHEMISTRY OF POLYMER FILMS NOT IMMERSED IN SOLUTION:  
ELECTRON TRANSFER ON AN ION BUDGET

Joseph C. Jernigan, Christopher E. D. Chidsey<sup>a</sup>  
and Royce W. Murray<sup>a</sup>

Kenan Laboratories of Chemistry  
University of North Carolina  
Chapel Hill, North Carolina 27514

ABSTRACT

Films of poly-[Os(bpy)<sub>2</sub>(vpy)<sub>2</sub>](ClO<sub>4</sub>)<sub>2</sub> sandwiched between two metallic electrodes can support electron hopping, concentration gradient-driven electron conduction in acetonitrile vapor and in dry N<sub>2</sub> gas, when the potential difference  $\Delta E$  between the electrodes is made such as to generate a mixture of Os(III), Os(II), and Os(I) states. The latter requirement is dictated by the fixed pool (ion budget) of ClO<sub>4</sub><sup>-</sup> counterions in the film. It is significant that ClO<sub>4</sub><sup>-</sup> ions can move relatively freely in the dry film, that the apparent Os(III/II) and Os(II/I) formal potentials are different for the vapor and dry N<sub>2</sub> environments, and that currents through dry polymer films are larger than in vapor-exposed films.

Accession For	NTIS GRA&I	<input checked="" type="checkbox"/>	<input type="checkbox"/>
	DTIC TAB	<input type="checkbox"/>	<input type="checkbox"/>
	Unannounced		
	Justification		
By	Distribution/		
	Availability Codes		
	Avail and/or		
	Special		
Dist			



This laboratory recently described<sup>1</sup> steady state electron conduction through sub-micron films of electroactive polymeric transition metal complexes sandwiched between two electrodes. Complexes like [Os(bpy)<sub>2</sub>(vpy)<sub>2</sub>](ClO<sub>4</sub>)<sub>2</sub> were electropolymerized<sup>2,3</sup> onto polished Pt overlaid with a porous film of evaporated Au, which was contacted by electrolyte solution containing reference and auxiliary electrodes. In this paper, we show that voltammograms with large limiting currents can be obtained for similarly prepared<sup>1</sup> Pt/poly-[Os(bpy)<sub>2</sub>(vpy)<sub>2</sub>](ClO<sub>4</sub>)<sub>2</sub>/Au sandwiches in the absence of an electrolyte solution, bathed only in acetonitrile vapor, or dry N<sub>2</sub> gas.

The essential features of the previous<sup>1</sup> sandwich voltammetry in electrolyte solution are summarized in Figs. 1A and 1B. Fig. 1A is a voltammogram where only E<sub>Pt</sub> is controlled (vs. SSCE), and shows waves for Os(III/II), Os(II/I), and Os(I/0) (formal) couples. In Fig. 1B, where E<sub>Pt</sub> and E<sub>Au</sub> are controlled (vs. SSCE), E<sub>Au</sub> at 0V and E<sub>Pt</sub> being varied, a steady state current-potential wave appears when E<sub>Pt</sub> passes each redox film electroactivity. In the wave at positive E<sub>Pt</sub>, for instance, a limiting current (i<sub>III/II</sub>) means that all of the polymer next to the Pt electrode is Os(III) and all that next to the Au electrode is Os(II) in the linear concentration gradients of Os(III) and Os(II) states in the film as in Fig. 1B inset. This i<sub>III/II</sub> limiting current is controlled by the rate of electron hopping between Os(III) and Os(II) sites and is proportional to the electron diffusion coefficient D<sub>O(III/II)</sub> of the Os(III/II) couple and inversely proportional to film thickness d.

Fig. 1C shows a Pt/poly-[Os(bpy)<sub>2</sub>(vpy)<sub>2</sub>](ClO<sub>4</sub>)<sub>2</sub>/Au sandwich in a two electrode cell bathed in acetonitrile vapor (sat'd, 25°C). No

flows until the potential  $\Delta E$  applied between the Pt and Au electrodes exceeds ca. 1.9V. Then, a reproducible, steady state voltammogram appears with an  $E_p = 2.02 \pm 0.01V$  (for 7 electrodes) which equals the difference between the formal potentials +0.73 and -1.32V of the Os(III/II) and Os(II/I) couples appearing in Figs. 1A and 1B.

We ascribe the electrical behavior in Fig. 1C to the production of Os(III) and Os(I) sites at Pt and Au electrodes, respectively. Without a bathing electrolyte solution, charge conservation requires that for each Os(II) site oxidized to Os(III) at the Pt electrode, another must be reduced to Os(I) (releasing a  $ClO_4^-$  counterion) at the Au electrode. This can be called an ion budget, to emphasize the coupling of the redox chemistry of the film to its fixed but evidently quite mobile pool of electroinactive  $ClO_4^-$  counterions.

The limiting current  $i_{III/I}$  in Fig. 1C can be related to that of the Os(III/II) wave ( $i_{III/II}$ ) in Fig. 1B with simple electron diffusion and charge conservation statements to give<sup>7</sup>

$$i_{III/I}/i_{III/II} = 1 + [D_{Os(II/I)}/D_{Os(III/II)}]^{1/2} \quad (1)$$

If the electron diffusion coefficients  $D_{Os(III/II)}$  and  $D_{Os(II/I)}$  for the Os(III/II) and Os(II/I) couples in Fig. 1C are assumed to be the same as those in acetonitrile liquid-bathed polymer in Fig. 1B, this equation predicts that  $i_{III/I}/i_{III/II} = 2.68$ , which is fairly close to the ratio observed in Fig. 1C and analogous experiments,  $2.1 \pm 0.4$  (avg. of 7 electrodes). Eq. 1 seems thus to give a good first order account of the vapor-bathed experiment. The same theory predicts that concentration profiles of Os(III), Os(II), and Os(I) sites in the film when the  $i_{III/I}$  is

flowing are as in Fig. 1C inset. The diagram contains the elements that Os(III) and Os(I) sites react quantitatively in the interior of the film to form Os(II) sites, whose position of maximum concentration is determined jointly by the ion budget and the relative values of  $D_{Os(III/II)}$  and  $D_{Os(II/I)}$  and occurs at  $[D_{Os(III/II)}]^{1/2} / \{ [D_{Os(III/II)}]^{1/2} + [D_{Os(II/I)}]^{1/2} \}$ .

As discussed previously for redox conductivity, Eq. 1 rests on electron conduction driven by concentration gradients of Os redox sites and not trans-film potential gradients. The electron conduction in Fig. 1C in respect differs from that discussed previously for dry mixed valent films. Also, we believe  $i_{III/I}$  and the electron diffusion coefficients in eq. 1 principally reflect electron rather than ionic mobilities in the polymer so  $i_{III/I}$  is additionally different from currents in polymer electrolyte with ion-blocking electrodes. The Fig. 1C experiment does find analog thin layer electrodes containing solutions of redox species as described by Bard and coworkers<sup>10</sup>.

Voltammetry of the same Pt/poly-[Os(bpy)<sub>2</sub>(vpy)]( $ClO_4$ )<sub>2</sub>/Au sandwich dry  $H_2$  gas shows (Fig. 1D) a recognizable wave even though solvent has been deliberately<sup>11</sup> added. The "dry" voltammogram does show significant differences from Fig. 1C. First, there is hysteresis between currents recorded when  $\Delta E$  is increasing vs. decreasing; this effect is less pronounced for slowly scanned  $\Delta E$ . Apparently,  $ClO_4^-$  counterions are mobile in the absence of acetonitrile vapor, and on the time scale of scans do not move rapidly enough first toward and then away from the Os sites of the film (upon its oxidation and reduction, respectively) to a true steady state currents and concentration profiles of Os sites. At  $i_{III/I}$  plateau, the  $ClO_4^-$  mobility should again become less significant.

relation to the electron diffusion rate. Secondly,  $E_3$  for both increasing and decreasing  $\Delta E$  scans,  $2.47 \pm 0.1$  V and  $2.14 \pm 0.05$  V (avg. for 8 electrodes), respectively, are both larger than that (2.02 V) for the vapor-bathed film of Fig. 1C. This suggests that one or both of the "dry" Os(III/II) and Os(III/I) formal potentials differs significantly from those of the vapor-solvated couples. Thirdly, limiting currents  $i_{III/I}$  in dry  $N_2$  (Fig. 1D) are  $2.5 \pm 0.6$  (avg of 7 electrodes) times larger than those in acetonitrile vapor (Fig. 1C). According to Eq. 1, this might occur either through an increase in  $D_e(II/I)$  or a decrease in  $D_e(III/II)$ . All three effects have interesting connotations but further experiments must elucidate their origin(s).

Low temperature voltammetry of a Pt/poly-[Os(bpy)<sub>2</sub>(vpy)<sub>2</sub>](ClO<sub>4</sub>)<sub>2</sub>/Au sandwich electrode in acetonitrile vapor (Fig. 1E) is similar to room temperature results (Fig. 1C) except for a slight hysteresis indicating lowered ClO<sub>4</sub><sup>-</sup> mobility and a depressed  $i_{III/I}$  limiting current showing that electron hopping is an activated process in the vapor-bathed film.

The significance of the experiments in Figs. 1C-E is that voltammetry that can be understood (at least to a first order) with a simple electron diffusion model, is observable in the absence of an electrolyte solution. This opens a variety of possibilities for probing how electron transfer events depend on their environment. An obvious requirement of the experiment is that electroactive material be a good ionic conductor. However two redox couples are not strictly required since one can, for instance, start with an Os(III/II) mixed valent film<sup>7</sup>.

**Acknowledgment.** This research was supported in part by grants from the Office of Naval Research and the National Science Foundation.

#### REFERENCES

- Present address: AT & T Bell Laboratories, Murray Hill, N.J.
- (a) Pickup, P.G.; Murray, R.W. *J. Am. Chem. Soc.* 1983, **105**, 4510; (b) Pickup, P.G.; Murray, R.W. *J. Electrochem. Soc.* 1984, **131**, 833; (c) Pickup, P.G.; Kutner, W.; Leidner, C.R.; Murray, R.W. *J. Am. Chem. Soc.* 1984, **106**, 1991.
- bpy = 2,2'-bipyridine; vpy = 4-vinylpyridine.
- Calvert, J.M.; Schmehl, R.H.; Sullivan, B.P.; Facci, J.S.; Meyer, T.J. Murray, R.W. *Inorg. Chem.*, 1983, **22**, 2151.
- Similar results are obtained in pure acetonitrile liquid, but because of an ionic impurity the limiting currents were less reproducible upon successive potential scans.
- Electroneutrality will not rigorously apply at the interphases between phases at equilibrium or at steady-state<sup>6</sup>. However, space charges will lead to minor deviations from the predictions made here. These deviations will be examined thoroughly in a future report<sup>7</sup>.
- Buck, R.P. in "Ion-Selective Electrodes in Analytical Chemistry", Vol. H. Freiser, Ed., Plenum, New York, 1978, Chapter 1.
- Jernigan, J.C.; Chidsey, C.E.D.; Murray, R.W., University of North Carolina, unpublished work, 1984.
- (a) Pittman, C. U.; Suryanarayanan, B. *J. Amer. Chem. Soc.* 1974, **96**, 79; (b) Cowan, D. O.; Park, J.; Pittman, C. U.; Sasaki, Y.; Mukherjee, T. K.; Diamond, N. A. *J. Amer. Chem. Soc.* 1972, **94**, 5110; (c) Cowan, D. O.; Kaufman, F. *J. Amer. Chem. Soc.* 1970, **92**, 219.

9. (a) Shriver, D. F.; Papke, B. L.; Ratner, M. A.; Dupon, R.; Wong, T., Brodwin, M. Solid State Ionics 1981, 5, 83; (b) Hardy, L. C.; Shriver, D. F. Macromolecules 1984, 17, 975.
10. (a) Loefer, D.; Bard, A. J. J. Electrochem. Soc. 1975, 122, 632; (b) Brilmyer, G. W.; Bard, A. J. J. Electrochem. Soc. 1980, 127, 104.
11. While the films have not been analysed, the procedure for making the Au electrode contact of the sandwich (see Figure legend) leads us to expect that after Au deposition the polymer contains little residual acetonitrile solvent.






Figure 1. Voltammetry of Pt/poly-[Os(bpy)<sub>2</sub>(vpy)<sub>2</sub>](ClO<sub>4</sub>)<sub>2</sub>/Au sandwich electrode in various media;  $S=31.2\text{mA}/\text{cm}^2$ ,  $\Gamma_{\text{Os}} = 2.95 \times 10^{-8}\text{mol}/\text{cm}^2$  (ca. 400 nm film). All voltammograms at 25°C obtained with the same electrode with a scan rate of 50mV/s except as noted. The electrode was thoroughly rinsed with CH<sub>3</sub>CN after electropolymerization, dried, and subjected to  $10^{-7}$  torr vacuum and moderate heating during Au evaporation. It was stored in a desiccator and then, in the order of the experiments, exposed to N<sub>2</sub> gas (Curve D), CH<sub>3</sub>CN vapor (Curve C), and electrolyte solution (Curves A and B). Curve A)  $i_{\text{Pt}}$  vs  $E_{\text{Pt}}$  in 0.1M Et<sub>4</sub>NClO<sub>4</sub>/CH<sub>3</sub>CN; Curve B)  $i_{\text{Pt}}$  vs  $E_{\text{Pt}}$  with  $E_{\text{Au}}=0\text{V}$  vs SSCE in 0.1M Et<sub>4</sub>NClO<sub>4</sub>/CH<sub>3</sub>CN; Curve C)  $i$  vs  $\Delta E$  between Pt and Au electrodes in dry N<sub>2</sub> saturated with acetonitrile vapor; Curve D)  $i$  vs  $\Delta E$  in dry N<sub>2</sub> gas; scan rate=2mV/s; Curve E)  $i$  vs  $\Delta E$  in dry N<sub>2</sub> saturated with CH<sub>3</sub>CN vapor at -34°C using a different sandwich electrode.

DATE  
FILMED  
-8